

# BRERA

## MIXED YARNS

Composition: 64%VI 15%PL 11%CO 10%LI

Dyeing: Yarn dyed

Weaving: Jacquard

Weight: 870 gr/ml

Abrasion: 22.000 cycles (UNI EN ISO 12947-2) | Fastness to light: ≥4 (UNI EN ISO 105-B02)

Pilling: 3 cycles (UNI EN ISO 12945-2)



02



13



04



08




11



12



07



10

